



Reference: 10097802
Country Ref.: 2PG201
EAN 13: 3427620102032



CONTACT

Markets and Products Information
rollingstock.business@lynxeogroup.com

CONTROL WIRES

Strictly halogen-free, FLAMEX® control wires combine the advantages of small size, lightweight, high chemical resistance and high mechanical properties. They are recommended for installation in all types of railway vehicles. A 125°C conductor temperature is allowed during 20,000 hours cumulative working time for EN 50306-2.

STANDARDS

Product EN 45545-2 (HL3)

Test EN 50305; EN 50306

DESIGN

1. Conductor

Flexible stranded tinned copper

2. Insulation

Thin wall halogen-free cross-linked material acc. EN 50306-2
 Colour: white

Example of marking: FLAMEX 239 EN 50306-2 - 300 V - 1 x cross-section - M - week/year

GUIDE TO USE

- Cabling rules are given in EN 50343 and EN 50355
- Permissible current carrying capacities: values and calculation method are given in EN 50343
- Bending radius:
 - Static use: 5 x outer cable diameter
 - For installation and occasional movements: 10 x outer cable diameter



Conductor flexibility
 Flexible stranded



Halogen free
 EN 60754-1 & EN 60684-2



Rated Voltage U_o/U
 (Um)
 300 / 300 V



Flame retardant
 EN 60332-1-2



Fire retardant
 EN IEC 60332-3-25
 (EN50305)



Smoke density
 EN/IEC 61034-2



Gases toxicity
 EN 50305-9.2



Operating temp.
 -40 ... 105 °C

CHARACTERISTICS**Construction characteristics**

Conductor material	Tin plated copper
Conductor flexibility	Flexible stranded
Insulation	Cross-linked compound
Halogen free	EN 60754-1 & EN 60684-2
Insulation colour	White

Dimensional characteristics

Conductor cross-section	2.5 mm ²
Stranding (No./mm)	
Conductor diameter (mm)	2.00
Minimum cable diameter	2.45 mm
Maximum cable diameter	2.85 mm
Approximate weight	26.5 kg/km

Electrical characteristics

Rated Voltage U _o /U (U _m)	300 / 300 V
Max. DC resistance of the conductor at 20°C	8.21 Ohm/km

Usage characteristics

Flame retardant	EN 60332-1-2
Fire retardant	EN IEC 60332-3-25 (EN50305)
Smoke density	EN/IEC 61034-2
Gases toxicity	EN 50305-9.2
Operating temperature, range	-40 ... 105 °C
Maximum operating temperature	105 °C
Overload maximum core temperature	125 °C
Chemical resistance	Excellent
Fire load	0.015 kWh/m